

## Features

Anodes available in High Pure and H-1 Commercial grade magnesium. Each anode has a plated steel core with 14 feet of #12 THHN insulated lead wire attached with silver solder. Packaged anodes have a backfill mixture consisting of 75% Gypsum, 20% Western Bentonite and 5% Sodium Sulphate. Applications include UST, Pipe, AST bottom or other carbon steel in contact with the soil.

**CPAN Magnesium**

| Part No.     | Size | Magnesium Material | Packaged Wt. Lbs | Part No.     | Size | Zinc Material | Packaged Wt. Lbs |
|--------------|------|--------------------|------------------|--------------|------|---------------|------------------|
| CPAN-08-HP09 | 9#   | High Pure          | 20.0             | CPAN-12-0001 | 1#   | S.H.G.        | 4.0              |
| CPAN-08-HP17 | 17#  | High Pure          | 54.0             | CPAN-12-0005 | 5#   | S.H.G.        | 11.0             |
| CPAN-08-HP24 | 24#  | High Pure          | 63.0             | CPAN-12-0008 | 8#   | S.H.G.        | 13.0             |
| CPAN-08-HP32 | 32#  | High Pure          | 66.0             | CPAN-12-0010 | 10#  | S.H.G.        | 19.0             |
| CPAN-08-HP48 | 48#  | High Pure          | 102.0            | CPAN-12-0015 | 15#  | S.H.G.        | 35.0             |
| CPAN-08-0009 | 9#   | H1 Mag             | 23.0             | CPAN-12-0018 | 18#  | S.H.G.        | 38.0             |
| CPAN-08-0017 | 17#  | H1 Mag             | 45.0             | CPAN-12-0030 | 30#  | S.H.G.        | 68.0             |
| CPAN-08-0032 | 32#  | H1 Mag             | 66.0             |              |      |               |                  |
| CPAN-08-0050 | 48#  | H1 Mag             | 101.0            |              |      |               |                  |

## Features

Anodes available in Special High Grade (S.H.G.) zinc. The S.H.G. Home zinc exceeds all industry requirements for chemical composition. Each anode has plated a plated steel core with 14 feet of #12 THHN insulated lead wire attached with silver solder. Packaged anode backfill is composed of 75% Gypsum, 20% Western Bentonite and 5% Sodium Sulphate. Applications include UST, piping, AST bottoms and other carbon steel in contact with the soil. Zinc anodes can be manufactured to your specific requirements.

**CPAN Zinc**